Compressive strength of 100 mm cubes of Natural Cement concrete after immersion in solutions A-G for 1 year

Compressive strength data given is the mean of results for 3 duplicate samples

Project report number 79886/M6
Commercial in confidence

©Building Research Establishment Ltd 2001

Solution Identity	Compressive strength after 28 days water curing. (Mpa)	Compressive strength after 1 year solution immersion. (Mpa)	Percentage of 28 days compressive strength	Percentage of compressive strength of sample stored in water for 1 year
A	47.5	81	171	99
B	47.5	83.5	176	102
C	47.5	80	168	98
D	47.5	85	179	104
E	47.5	81	171	99
F	47.5	83	175	102
G (water)	47.5	81.5	172	100

Natural Cement Distribution Ltd.,
10-11 Fountain Parade, Mapplewell, Barnsley. S75 6FW
Tel: 01226 381133 Fax: 01226 381177 www.naturalcement.co.uk