# COMPRESSIVE STRENGTH OF SHOTCRETE 530




| | |
|---|---|
| 0.5 hour | 0.6 |
| 1 hour | 4.1 |
| 1.5 hours | 11.5 |
| 2 hours | 15 |
| 2.5 hours | 18.8 |
| 3 hours | 19.9 |
| 3.5 hours | 22.5 |
| 4 hours | 24.3 |
| 4.5 hours | 24.5 |
| 5 hours | 24.8 |

**TEST PROGRAMME PREPARED BY:**
**DR K.E. Hassan - Civil Engineering Materials Unit (CEMU)**
**School of Civil Engineering, University of Leeds**

**Natural Cement Distribution Ltd.**
10-11 Fountain Parade, Mapplewell, Barnsley. S75 6FW
Tel: 01226 381133 Fax: 01226 381177 www.naturalcement.co.uk