Kiwa CMT

Kiwa CMT Testing
Unit 5 Prime Park Way
Prime Enterprise Park
Derby
DE1 3QB

T +44 (0)1332 383333
F +44 (0)1332 602607
E cmtenquiries@kiwa.co.uk

www.kiwa.co.uk/cmt

Central Midlands Laboratories
32 Woodmeadow Road
Kings Norton
Birmingham
B30 3PD

Date:	20th April 2021
Lab Ref:	62951
Order Ref:	CML 280
Originator:	Nick Collier
Site:	N/A Trackcrete.
Samples:	2 x 25kg bags of Trackcrete material were delivered, by the client, to Kiwa CMT on the 7th April 2021.
Requirements:	To mix the material at a water solids ratio of 0.08 (8.0%) and produce 1 set of prisms to be tested at 24 hours for Density, Flexural Strength and Compressive strength in accordance with BSEN1015-11.
Results:	Detailed test results and information are appended.

Kiwa CMT Testing

G. Peach AMICT
Department Manager
Building Products

Kiwa CMT

Results:

Density, Flexural Strength and Compressive Strength (24 hours after casting)

Ref	Cast Date	Test Date	Density (Kg/m³)	Flexural Strength (N/mm²)	Compressive Strength (N/mm²)	Compressive Strength (N/mm²)
Trackcrete (1d)	19/04/21	20/04/21	2326	6.59	34.8	34.6
Trackcrete (1d)	19/04/21	20/04/21	2328	7.42	34.0	36.1
Trackcrete (1d)	19/04/21	20/04/21	2357	6.36	33.4	34.4
		Av	**2335**	**6.79**	**Av**	**34.6**

Kiwa CMT Testing

G. Peach AMICT
Department Manager
Building Products