Triflex (UK) Limited | Whitebridge Way | Stone | Staffordshire | ST15 8JS

To whom it may concern

Triflex (UK) Limited
Whitebridge Way
Stone
Staffordshire
ST15 8JS
Tel: 01785 819119
Fax: 01785 819960
info@triflex.co.uk
www.triflex.co.uk

Paul Barker
Director

Tel: 01785 819119
Fax: 01785 819960

17.05.2013

Triflex compatibility with Natcem 35

Compatibility

Test basis:

- Accelerated ageing at +80°C for 4 weeks
- Storage under water at +20°C for 4 weeks
- Practical experience on thousands of m^2 (earliest project 2005)

Primer: Triflex Cryl Primer 276

Results: **Compatible**

Overlay times

Practical experience: Natcem 35 has been successfully overlaid with Triflex materials after 1 hour.

Recommendations: The Natcem 35 should be allowed to harden and hydrate sufficiently to achieve a surface compressive strength when tested with a rebound hammer in excess of 25N/mm^2 prior to overlay with Triflex systems.

Yours sincerely

Paul Barker
Director
Triflex (UK) Limited